202 434 1501

Serial No. 10/657,193

IN THE CLAIMS:

The text of all pending claims, (including withdrawn claims) is set forth below. Cancelled and not entered claims are indicated with claim number and status only. The claims as listed below show added text with <u>underlining</u> and deleted text with <u>etrikethrough</u>. The status of each claim is indicated with one of (original), (currently amended), (cancelled), (withdrawn), (new), (previously presented), or (not entered).

Please AMEND claim 1 in accordance with the following:

1. (CURRENTLY AMENDED) A method of forming a conductor wiring pattern, comprising the following steps of:

forming a first insulating layer on a surface of a substrate and also-forming a second, photosensitive insulating resin layer thereon;

light-exposing and developing the second insulating layer to form pattern grooves so that the first insulating layer is exposed at bottoms of the pattern grooves;

forming a plating seed layer on the second insulating layer including inner surfaces of the pattern grooves and then forming a resist pattern on the plating seed layer except for portions of the pattern grooves of the second insulating layer so that the seed layer in conformity with the pattern grooves is exposed;

filling the pattern grooves with a conductor by an electrolytic plating using the plating seed layer as a power supply layer; and

removing the resist pattern and also removing the seed layer exposed on the surface of the second insulating layer to form <u>a</u> wiring pattern consisting of conductors remained remaining in the pattern grooves.

- 2. (ORIGINAL) A method as set forth in claim 1, wherein a plurality of different metal layers are used, as the conductor, when the pattern grooves are filled with the conductor by the electrolytic plating.
- (ORIGINAL) A method as set forth in claim 2, wherein the plurality of different
 metal layers are at least two metal layers consisting of a copper base layer and a nickel barrier
 layer.

BEST AVAILABLE COPY

Serial No. 10/657,193

- (CURRENTLY AMENDED) A method as set forth in claim 1, wherein: the first insulating layer is composed of a photosensitive insulating resin;
- and after the first insulating layer is light-exposed and developed to form an opening, through which a first wiring pattern formed on the substrate is to be electrically connected to a second wiring pattern to be formed on the first insulating layer, the first insulating layer is heated and hardened.
- (ORIGINAL) A method as set forth in claim 1, wherein a semiconductor wafer is 5. used as the substate, the semiconductor wafer has an electrode terminal forming surface, on which the first insulating layer and the second insulating layer are formed, and the wiring pattern, which is electrically connected with electrode terminals of the semiconductor wafer, is formed.

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:	
□ BLACK BORDERS	
☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES	
☐ FADED TEXT OR DRAWING	
☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING	
☐ SKEWED/SLANTED IMAGES	
☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS	
GRAY SCALE DOCUMENTS	
☐ LINES OR MARKS ON ORIGINAL DOCUMENT	
☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY	
Потикв.	

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.